



FOR A BETTER WORLD

Plasterboard Liner Brown Grades

Typical Values

Property	Unit	PB160	PB170	PB180	PB200	PB220
Grammage	g/m ²	160	170	180	200	220
Tensile Strength – MD	kN/m	11.7	11.9	12.1	12.5	12.9
Tensile Strength – CD	kN/m	4.3	4.4	4.5	4.7	4.9
Air Permeance (Gurley)	sec	40	40	40	40	40
Cobb – 1min Top	g/m ²	24	24	24	22	22
Cobb – 1 min Back	g/m ²	22	22	22	22	22



FOR A BETTER WORLD

Plasterboard Liner Ivory Grades

Typical Values

Property	Unit	PV170	PV180	PV190	PV200	PV210	PV220
Grammage	g/m ²	170	180	190	200	210	220
Tensile Strength – MD	kN/m	11.9	12.1	12.3	12.5	12.7	12.9
Tensile Strength – CD	kN/m	4.3	4.4	4.5	4.6	4.7	4.8
Air Permeance (Gurley)	sec	40	40	40	40	40	40
Cobb – 1min Top	g/m ²	22	22	22	22	22	22
Cobb – 1 min Back	g/m ²	22	22	22	22	22	22
Brightness	ISO	52	52	52	52	52	52



FOR A BETTER WORLD

Plasterboard Coloured Grades

Typical Values

Colour		Blue				Pink			Green		Purple	Yellow	
Property	Unit	PL170F	PL180F	PL190F	PL220F	PP170F	PP180F	PP190F	PG180F	PG220F	PU220F	PY170F	PY220F
Grammage	g/m ²	170	180	190	220	170	180	190	180	220	220	170	220
Tensile Strength – MD	kN/m	11.9	12.1	12.3	13.0	11.9	12.1	12.3	12.1	13.0	13.0	11.9	13.0
Tensile Strength – CD	kN/m	4.3	4.4	4.5	4.8	4.3	4.4	4.5	1.5	4.8	4.8	4.3	4.8
Air Permeance (Gurley)	sec	40	40	40	40	40	40	40	40	40	40	40	40
Cobb – 1min Top	g/m ²	22	22	22	22	22	22	22	22	22	22	22	22
Cobb – 1 min Back	g/m ²	22	22	22	22	22	22	22	22	22	22	22	22